

# PROFESSIONAL HEAVY DUTY ANTIFREEZE/ COOLANT

LOW SILICATE • PHOSPHATE FREE • FULLY FORMULATED

## **CLASSIC** CONVENTIONAL DIESEL

# CLASSIC FORMULATION. EXCELLENT VALUE.

Featuring HD Expert's legacy technology, Classic is a traditional coolant ideally suited for older vehicles.

### FORMULATION FEATURES & BENEFITS:

**Wide Application:** The low silicate level of this aluminum compatible product allows it to be used in automotive, light duty, heavy duty diesel and natural gas engine (NGE) applications such as on-road truck, off-road and farm equipment. This includes, but is not limited to, Caterpillar, Cummins, Detroit Diesel, Ford, Freightliner, GM, International Truck and Engine, Kenworth, Paccar, Peterbilt, Volvo Mack, Western Star and other HD and industrial application where a conventional HD coolant is required.

**Proven Protection:** Classic Conventional Diesel is based on traditional inorganic inhibitors, including silicates, nitrites and borates. It is phosphate and amine free, specifically formulated to protect wet sleeve cylinder liners from erosion, pitting and system metal corrosion in heavy duty applications. Scale preventative additives counter the negative effects of hard water to ensure optimal heat transfer is maintained.

**Field Compatibility:** It is miscible and compatible with any other traditional fully formulated, conventional coolant products, standard heavy duty SCAs and coolant filters. Recommended for use where a fully formulated heavy duty diesel coolant is required, this pre-charged product does not require an initial charge of Supplemental Coolant Additives (SCA) and is hard water tolerant.

All Climate Performance: Provides protection against low temperature freeze-up or high temperature boil-over and suitable for all season use throughout winter and summer. When used as 50% diluted with high quality water, provides freeze protection down to  $-37^{\circ}$ C/ $-34^{\circ}$ F and boil-over protection up to  $+132^{\circ}$ C/ $+269^{\circ}$ F (with the use of a 100 kPa pressure cap). Available in Concentrate and 50-50 Pre-diluted formats.









**CLASSIC Conventional Diesel** protects heavy duty diesel wet sleeve liners and is based on a proprietary formulation of corrosion inhibitors. A traditional coolant ideally suited for older vehicles, Classic is recommended for use where a fully formulated heavy duty diesel coolant is required. This includes, but is not limited to, Caterpillar, Cummins, Detroit Diesel, Ford, Freightliner, GM, International Truck and Engine, Kenworth, Paccar, Peterbilt, Volvo Mack and Western Star.

| Meets or exceeds performance<br>requirements of: | Recommended and suitable for use with: |                           |  |  |
|--|--|---------------------------|--|--|
| • ASTM D3306, D6210                              | • Caterpillar                          | • Mack                    |  |  |
| • AS/NZS 2108.2004 Type A                        | • CNHi MAT 3620                        | Navistar MPAPS B-1 Typ II |  |  |
| • CNHi MAT 3720                                  | Cummins CES 14603 / 14439 / 3666132    | • PACCAR                  |  |  |
| Detroit Diesel Fluid Specification               | • Ford ESE-M97B44-A, ESE-M97B44-C      | • Peterbilt               |  |  |
| DFS93K217SLC                                     | • GM 1825M, 1899M                      | Volvo Heavy Truck         |  |  |
| • GB 29743-2013                                  | • GM Heavy Truck                       |                           |  |  |
|  | International Truck                    |                           |  |  |
| • JCB  | • Kenworth                             |                           |  |  |
| • New Flyer eBus • TMC RP329B                    | • Kubota                               |                           |  |  |

### **Typical Physical and Chemical Characteristics**

| CHARACTERISTIC                             | PERFOR                                   | TEST METHOD                 |            |
|--|--|-----------------------------|------------|
|  | CONCENTRATE                              | 50-50 PREMIX                |            |
| Appearance                                 | Clear and transparent<br>fluid           | Clear and transparent fluid |            |
| Colour                                     | Purple                                   | Purple                      |            |
| pН   | 10.0 - 11.0                              | 10.0 - 11.0                 | ASTM D1287 |
| Reserve Alkalinity                         | 8.0 min.                                 | 4.0 min.                    | ASTM D1121 |
| Specific gravity                           | 1.115 – 1.135                            | 1.065 - 1.085               | ASTM D1122 |
| Freeze point, °C/°F                        | 60/40: -52/-61<br>70/30: -64/-83 -37/-34 |                             | ASTM D1177 |
| Foam volume, ml                            | 50 max.                                  | 50 max.                     | ASTM D1881 |
| Foam break time, second                    | 5 max.                                   | 5 max.                      | ASTM D1881 |
| Chloride, ppm                              | < 25                                     | < 25                        | ASTM D3634 |
| Phosphate                                  | < 10                                     | < 10                        | ASTM D5827 |
| Shelf Life, (Unopened, original container) | 2 years                                  | 2 years                     |            |

These characteristics are typical of current production. While future production will conform to Recochem's specification, variations in these characteristics may occur.







Dated: Sep'22



### **Dilution Chart**

| Protection against Freezing (°C/°F)    | -37 / -34 | -52 / -61 | -64 / -83 |
|--|-----------|-----------|-----------|
| Volume % Antifreeze                    | 50        | 60        | 70        |
| Volume % Deionized Water               | 50        | 40        | 30        |
| **Protection against Boil-Over (°C/°F) | 129 / 264 | 132 / 269 | 136 / 276 |

\*\*\*with a 100 kilopascals (15 psi) radiator cap in good condition

Coolant concentrate must be diluted with water prior to use. Antifreeze/Coolant should not be used in concentrated form. A 50% dilution is generally recommended for the best balance of protection against freezing, corrosion and summer boil-over. For increased freeze protection in extremely cold areas, a 60% volume concentration can be used. Concentrations of greater than 70% by volume are not recommended. High quality soft, de-ionized or distilled water should always be used to dilute coolant concentrate.

### **Typical Coolant Performance Testing Results**

| Metal Type |                           | D 1384<br>CORROSION | ASTM D 2570<br>SIMULATED SERVICE |            |
|------------|---------------------------|---------------------|----------------------------------|------------|
|            | Test Results <sup>1</sup> | Max. Spec.          | Test Results <sup>1</sup>        | Max. Spec. |
| Copper     | 1                         | 10                  | -1                               | 20         |
| Solder     | 4                         | 30                  | 14                               | 60         |
| Brass      | 1                         | 10                  | 2                                | 20         |
| Steel      | 1                         | 10                  | 0                                | 20         |
| Cast Iron  | -5                        | 10                  | -6                               | 20         |
| Aluminum   | -2                        | 30                  | 1                                | 60         |

<sup>1</sup> Weight loss, except minus signs which indicate weight gain, per coupon in milligrams. Values are for coolant made from virgin ethylene glycol.

### **Typical Coolant Performance Testing Results (continued)**

|  | Test Results | Specification |
|--|--------------|---------------|
| ASTM D4340 Heat Rejecting Aluminum Corrosion<br>(mg/cm²/week) <sup>2</sup> | 0.2          | 1.0 maximum   |
| ASTM D2809 Aluminum Water Pump<br>Cavitation- Erosion Corrosion Rating     | 8            | 8 minimum     |

Weight loss per coupon in milligrams (average for 2 tests). Values are for coolant made from virgin ethylene glycol









### PROFESSIONAL HEAVY DUTY ANTIFREEZE/COOLANT

### **Product Packaging Specifications**

### CANADA

| Item No. | Formulation    | Container Size | Case<br>Pack | UPC             | SCC               |
|----------|----------------|----------------|--------------|-----------------|-------------------|
| 16-284   | Concentrate    | 3.78 L         | 4            | 0-56438-16284-1 | 400-56438-16284-9 |
| 16-474   | 50-50 premixed | 3.78 L         | 4            | 0-56438-16474-6 | 400-56438-16474-4 |
| 16-285   | Concentrate    | 9.46 L         | 2            | 0-56438-16285-8 | 500-56438-16285-3 |
| 16-475   | 50-50 premixed | 9.46 L         | 2            | 0-56438-16475-3 | 500-56438-16475-8 |

### USA

| Item No. | Formulation       | Container Size | Case<br>Pack | UPC             | SCC               |
|----------|-------------------|----------------|--------------|-----------------|-------------------|
| 86-284   | Concentrate       | 1 gal          | 4            | 0-56438-86284-0 | 400-56438-86284-8 |
| 86-474   | 50-50 pre-diluted | 1 gal          | 4            | 0-56438-86474-5 | 400-56438-86474-3 |

### DRUM/TOTE

| Item No.    | Formulation    | Container Size   | Case<br>Pack | UPC             | SCC |
|-------------|----------------|------------------|--------------|-----------------|-----|
| 26-289      | Concentrate    | 208 L / 55 gal   | NA           | 0-56438-26289-3 | NA  |
| 26-479      | 50-50 premixed | 208 L / 55 gal   | NA           | 0-56438-26479-8 | NA  |
| 26-289-1000 | Concentrate    | 1000 L / 264 gal | NA           | 0-56438-90787-9 | NA  |
| 26-479-1000 | 50-50 premixed | 1000 L / 264 gal | NA           | 0-56438-90788-6 | NA  |

### Warrantee:

When added as an initial fill and properly maintained in accordance with engine manufacturer's maintenance recommendation, this product will provide an in-service life of up to 2500 hrs or 2 years, whichever comes first. While deleterious effects are not expected to be significant, mixing with conventional coolants will result in a lower than expected lifetime.

### Handling, Storage & Shelf Life

Product should be stored in original container or appropriate dedicated tank or vessel. Although temperature fluctuations will not adversely affect coolant, unused coolant should be stored at ambient conditions. Under typical conditions and when the container integrity is maintained, product can be stored for up to 2 years without any adverse effect on quality. Product should be agitated before use.

### Health, Safety & Environment

For detailed information and recommended practices related to Health and Safety, please refer to the appropriate Safety Data Sheet (SDS).

New or spent coolant is never to be disposed of into a septic system, storm sewer or onto the ground. Always dispose coolant in accordance with local, provincial/ state and federal guidelines. Contain any spilled coolant and contact appropriate authorities on appropriate clean-up instructions.

NOTICE: This product is shipped in compliance with applicable laws and regulations regarding classification, packaging, shipping and handling. The performance and physical property data described for this product are typical results not sale specifications, except where maximum or minimum is indicated. Refer to Safety Data Sheets for further information.

Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether product and the information in this document are appropriate for their use and for ensuring that their workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Recochem's warranty is limited to the claims of product meeting stated performance specifications. It is the responsibility of the end-user to determine product suitability as recommended in the owner's manual and to follow engine manufacturer's instructions.





